



CheMarCo, Inc
P.O. Box 27065
Greenville, SC 29616

(864) 234-6735 Phone
(864) 234-6975 Fax

Technical Data Sheet

LIQUID EPOXY RESIN BE-501-X-75

BE-501-X-75 is a solid epoxy resin diluted with 25% Xylene. The resin is suitable for most general-purpose coatings applications, and is generally cured with polyamine or polyamide hardeners.

SPECIFICATIONS

Epoxy Equivalent Weight (EEW)	470-530
Viscosity, Brookfield, cps, 25° C	7000-14000
Color, Gardner	1 maximum
Solids, %	74-76

APPLICATIONS

- Coatings for metal, glass, wood and concrete
- Pipe and drum linings
- General maintenance coatings

Comparable Products

Based on Literature data. Products must be evaluated for specific formulation applicability.

- D.E.R. 671-X75
- Epon 1001-X-75

STORAGE

BE-501-X-75 should be stored in a dry place away from sources of heat. Under these conditions, the resin has a storage life of at least one-year. BE-501-X-75 is flammable and should be handled and stored using appropriate caution.

PACKAGING

- Net 500 pounds in steel drums; total of 72 drums (36,000 pounds) per container.