



**CheMarCo, Inc**

P.O. Box 27065  
Greenville, SC 29616

Phone: (864) 234-6735

Fax: (864) 234-6975

E-mail: sales@chemarco.com

# Technical Data Sheet

## LIQUID EPOXY RESIN CMC-1507

### SPECIFICATIONS

Epoxy Equivalent Weight (EEW)	180-192
Viscosity, Brookfield, cps, 25°C	500-800
Color, Gardner, max.	2-3
Specific Gravity	1.12-1.15

### APPLICATION

- Protective Coatings
- Casting
- Hand Lay-up Laminating
- Impregnations
- Adhesives
- Decoupage

### STORAGE

CMC-1507 should be stored in dry place away from sources of heat. Under these conditions, the resin has a storage life of at least one-year.